



JOLIN CORPORATION

大连九霖科技发展有限公司

Tel: +86-411-82479399/ 82479385/ 82479386

Fax: +86-411-82479390

[http:// jolingroup.com](http://jolingroup.com)

Email: jolin@jolingroup.com

Item

Product Description Photoluminescent pigment
 Model YG-FA6-RW

Application Scopes

Brush paint indoors/outdoors, toys and arts, etc.

Typical chemical properties

Composition Strontium Aluminate dopped with Europium Dysprosium oxides.
 Insoluble in organic solvents, water
 Decomposition by Strong acids, strong alkalines
 Fastness to heat -40~500°C

Typical physical properties

Appearance Yellowish crystal powder
 Specific gravity 3.6g/cm³
 Bulk Density 1.21g/cm³
 Particle size distribution D10: 140~150um 100% passing 250mesh.

Typical luminescent properties

Excitation all visible light and UV light (200~450nm better)
 Glow Color Yellow green (Emitting light Wavelength Peak: 520±2nm)
 Afterglow Intensity after 10min >1150 mcd/m²
 60min >160 mcd/m²
 600min >10 mcd/m²

Afterglow intensity(to 0.32mcd/m²): >14500min under norm DIN67 510

Typical luminance data

| Time | 10" | 1' | 2' | 3' | 4' | 5' | 10' | 15' | 20' | 30' | 40' | 50' | 60' | 90' | 120' | 180' | 300' | 600' |
|--------------------|-------|------|------|------|------|------|------|-----|-----|-----|-----|-----|-----|-----|------|------|------|------|
| mcd/m ² | 22040 | 8773 | 5323 | 3846 | 3012 | 2478 | 1271 | 863 | 629 | 392 | 277 | 211 | 168 | 106 | 75.1 | 46.6 | 25.8 | 11.6 |

| | |
|----------------------------|--|
| Luminance Test Methods | <p>Under Norm DIN67510-1:2009</p> <p>Put sample in opaque container for 24hrs, Temperature: 23±2°C, expose the sample under 1000lx-D65 light source for 5', then turn off the light and test the sample's afterglow luminance at 2', 10', 30', and 60'.</p> |
| Luminance Test Instruments | <ul style="list-style-type: none"> ○ Charging Light Source D65 Xenon Lamp ○ Charging Lamp Model Toshiba FL20S.D-EDL-D65 ○ Test Instruments Model Luminance Meter: Konica Minolta LS-150 Illuminance Meter: Konica Minolta T-10A |

Lifespan: >15years under well packing condition.

Safety:

1. Toxic: NO.

2. Radioactive: NO.

Other data:

1. Using Condition(recommended):
With all colorless, transparent medium, such as paint, coating, resin, etc.
2. Storage Condition: In cool, dry and ventilated place, with temperature -50~60°C
3. Packing: 25kgs /iron pail lined with plastic bags.
G.W.: 26.6kgs, Dim: D31 x H34cm

- 20'Container FCL Q'ty: 11250kgs(palletized)
4. Norm Complied: EN71-3, RoHS, DGM.
5. Norm MEET: PSPA Class-E, JIS-Z9107 JC.
IMO A.752(18), ISO 23601, UL924,
ASTM E2030/E2072/E2073,
ATPA SS-PS-002-98/SS-PS-004-99,
BS 5499-1 2002, NYC Law 26