



# JOLIN CORPORATION

大连九霖科技发展有限公司

Tel: +86-411-82479399/ 82479385/ 82479386

Fax: +86-411-82479390

[http:// jolingroup.com](http://jolingroup.com)

Email: [jolin@jolingroup.com](mailto:jolin@jolingroup.com)

## Item

Product Description	Photoluminescent pigment
Model	YG-B5

## Application Scopes

Brush/roller/spray paint indoors, screen printing, signs, castling plastic, silicone rubber, toys and arts, etc.

## Typical chemical properties

Composition	Strontium Aluminate dopped with Europium Dysprosium oxides.
Insoluble in	organic solvents
Decomposition by	Strong acids, strong alkalines, water
Fastness to heat	-40~500°C

## Typical physical properties

Appearance	Yellowish crystal powder	
Specific gravity	3.6g/cm <sup>3</sup>	
Bulk Density	1.04g/cm <sup>3</sup>	
Particle size distribution	15~25um.	100% passing 300mesh.

## Typical luminescent properties

Excitation	all visible light and UV light (200~450nm better)		
Glow Color	Yellow green (Emitting light Wavelength Peak: 520±2nm)		
Afterglow Intensity after	10min	>200	mcd/m <sup>2</sup>
	60min	>26.0	mcd/m <sup>2</sup>
	600min	>1.40	mcd/m <sup>2</sup>

Afterglow intensity(to 0.32mcd/m<sup>2</sup>): >2140min under norm DIN67 510

## Typical luminance data

Time	10"	1'	2'	3'	4'	5'	10'	15'	20'	30'	40'	50'	60'	90'	120'	180'	300'	600'
mcd/m <sup>2</sup>	6131	1827	1032	719	551	447	225	147	107	67.3	47.7	36.3	29.1	17.5	12.2	7.3	3.83	1.54

Luminance Test Methods	<p>Under Norm DIN67510-1:2009</p> <p>Put sample in opaque container for 24hrs, Temperature: 23±2°C, expose the sample under 1000lx-D65 light source for 5', then turn off the light and test the sample's afterglow luminance at 2', 10', 30', and 60'.</p>
Luminance Test Instruments	<ul style="list-style-type: none"> <li>○ Charging Light Source D65 Xenon Lamp</li> <li>○ Charging Lamp Model Toshiba FL20S.D-EDL-D65</li> <li>○ Test Instruments Model Luminance Meter: Konica Minolta LS-150 Illuminance Meter: Konica Minolta T-10A</li> </ul>

**Lifespan:** >15years under well packing condition.

**Safety:**

1. Toxic: NO.

2. Radioactive: NO.

**Other data:**

1. Using Condition(recommended):  
With all colorless, transparent medium, such as paint, coating, resin, etc.
2. Storage Condition: In cool, dry and ventilated place, with temperature -50~60°C
3. Packing: 25kgs /iron pail lined with plastic bags.  
G.W.: 26.6kgs, Dim: D31 x H34cm

- 20'Container FCL Q'ty: 11250kgs(palletized)
4. Norm Complied: EN71-3, RoHS, DGM.
5. Norm MEET: PSPA Class-E, JIS-Z9107 JC.  
IMO A.752(18), ISO 23601, UL924,  
ASTM E2030/E2072/E2073,  
ATPA SS-PS-002-98/SS-PS-004-99,  
BS 5499-1 2002, NYC Law 26