



JOLIN CORPORATION

大连九霖科技发展有限公司

Tel: +86-411-82479399/ 82479385/ 82479386

Fax: +86-411-82479390

[http:// jolingroup.com](http://jolingroup.com)

Email: jolin@jolingroup.com

Item

Product Description Photoluminescent pigment
 Model PR-B2-RW

Application Scopes

Screen printing ink, brush/roller/spraying paint indoors, dip plastic coating, injection/extrusion/casting plastic, silicone rubber molding, etc.

Typical chemical properties

Composition Strontium Aluminate dopped with Europium Dysprosium oxides.
 Insoluble in organic solvents
 Decomposition by Strong acids, strong alkalines
 Fastness to heat -40~230°C

Typical physical properties

Appearance Pink red crystal powder
 Specific gravity 3.6g/cm³
 Bulk Density 1.21g/cm³
 Average Particle Size 100~120um 100% pass 100mesh.

Typical luminescent properties

Excitation all visible light and UV light (200~450nm better)
 Glow Color Pink Red
 Afterglow Intensity after 10min >150 mcd/m²
 60min >20.0 mcd/m²
 600min >1.22 mcd/m²

Afterglow intensity(to 0.32mcd/m²): >1810min under norm DIN67 510

Typical luminance data

Time	10"	1'	2'	3'	4'	5'	10'	15'	20'	30'	40'	50'	60'	90'	120'	180'	300'	600'
mcd/m ²	4144	1303	738	516	392	319	160	105	76.7	48.1	34	25.8	20.3	12.4	8.69	5.34	2.87	1.32

Luminance Test Methods	<p>Under Norm DIN67510-1:2009</p> <p>Put sample in opaque container for 24hrs, Temperature: 23±2°C, expose the sample under 1000lx-D65 light source for 5', then turn off the light and test the sample's afterglow luminance at 2', 10', 30', and 60'.</p>
Luminance Test Instruments	<ul style="list-style-type: none"> ○ Charging Light Source D65 Xenon Lamp ○ Charging Lamp Model Toshiba FL20S.D-EDL-D65 ○ Test Instruments Model Luminance Meter: Konica Minolta LS-150 Illuminance Meter: Konica Minolta T-10A

Lifespan: >15years under well packing condition.

Safety:

1. Toxic:

2. Radioactive: NO.

Other data:

1. Using Condition(recommended):

With all colorless, transparent medium, such as paint, coating, resin, etc.

20'Container FCL Q'ty: 11250kgs(palletized)

2. Storage Condition: In cool, dry and ventilated place, with temperature -50~60°C

4. Norm Complied: EN71-3, RoHS, DGM.

3. Packing: 25kgs /iron pail lined with plastic bags.
G.W.: 26.6kgs, Dim: D31 x H34cm

5. Norm MEET: PSPA Class-E, JIS-Z9107 JC.

IMO A.752(18), ISO 23601, UL924,
ASTM E2030/E2072/E2073,
ATPA SS-PS-002-98/SS-PS-004-99,
BS 5499-1 2002, NYC Law 26