



JOLIN CORPORATION

大连九霖科技发展有限公司

Tel: +86-411-82479399/ 82479385/ 82479386

Fax: +86-411-82479390

<http://jolingroup.com>

Email: jolin@jolingroup.com

Item

Product Description Photoluminescent pigment
Model B-B3

Application Scopes

Screen printing ink, brush/roller/spraying paint indoors, dip plastic coating, injection/extrusion/casting plastic, silicone rubber molding, etc.

Typical chemical properties

Composition Strontium Aluminate dopped with Europium Dysprosium oxides.
Insoluble in organic solvents
Decomposition by organic solvents
Fastness to heat -40~230°C

Typical physical properties

Appearance Blue crystal powder
Specific gravity 3.6g/cm³
Bulk Density 1.21g/cm³
Average particle size 20~30um. 100% passing 200mesh.

Typical luminescent properties

Excitation all visible light and UV light (200~450nm better)
Glow Color Dark Blue
Afterglow Intensity 10min >110 mcd/m²
after 60min >12.4 mcd/m²
 600min >0.95 mcd/m²

Afterglow intensity(to 0.32mcd/m²): >2220min under norm DIN67 510

Typical luminance data

Time	10"	1'	2'	3'	4'	5'	10'	15'	20'	30'	40'	50'	60'	90'	120'	180'	300'	600'
mcd/m ²	1968	882	586	436	301	238	119	67.4	45.2	32.1	25.2	18.5	13.2	9.89	6.91	4.96	2.41	1.06

Luminance Test Methods	<p>Under Norm DIN67510-1:2009</p> <p>Put sample in opaque container for 24hrs, Temperature: 23±2°C, expose the sample under 1000lx-D65 light source for 5', then turn off the light and test the sample's afterglow luminance at 2', 10', 30', and 60'.</p>
Luminance Test Instruments	<ul style="list-style-type: none"> ○ Charging Light Source D65 Xenon Lamp ○ Charging Lamp Model Toshiba FL20S.D-EDL-D65 ○ Test Instruments Model Luminance Meter: Konica Minolta LS-150 Illuminance Meter: Konica Minolta T-10A

Lifespan: >15years under well packing condition.

Safety:

1. Toxic:

2. Radioactive: NO.

Other data:

1. Using Condition(recommended):

With all colorless, transparent medium, such as paint, coating, resin, etc.

20'Container FCL Q'ty: 11250kgs(palletized)

4. Norm Complied: EN71-3, RoHS, DGM.

5. Norm MEET: PSPA Class-E, JIS-Z9107 JC.

2. Storage Condition: In cool, dry and ventilated place, with temperature -50~60°C

IMO A.752(18), ISO 23601, UL924, ASTM E2030/E2072/E2073,

3. Packing: 25kgs /iron pail lined with plastic bags.
G.W.: 26.6kgs, Dim: D31 x H34cm

ATPA SS-PS-002-98/SS-PS-004-99, BS 5499-1 2002, NYC Law 26