

Luminance Test Methods	<p>Under Norm DIN67510-1:2009</p> <p>Put sample in opaque container for 24hrs, Temperature: 23±2°C, expose the sample under 1000lx-D65 light source for 5', then turn off the light and test the sample's afterglow luminance at 2', 10', 30', and 60'.</p>
Luminance Test Instruments	<ul style="list-style-type: none"> ○ Charging Light Source D65 Xenon Lamp ○ Charging Lamp Model Toshiba FL20S.D-EDL-D65 ○ Test Instruments Model Luminance Meter: Konica Minolta LS-150 Illuminance Meter: Konica Minolta T-10A

Lifespan: >15years under well packing condition.

Safety:

1. Toxic:

2. Radioactive: NO.

Other data:

1. Using Condition(recommended):

With all colorless, transparent medium, such as paint, coating, resin, etc.

20'Container FCL Q'ty: 11250kgs(palletized)

2. Storage Condition: In cool, dry and ventilated place, with temperature -50~60°C

4. Norm Complied: EN71-3, RoHS, DGM.

3. Packing: 25kgs /iron pail lined with plastic bags.
G.W.: 26.6kgs, Dim: D31 x H34cm

5. Norm MEET: PSPA Class-E, JIS-Z9107 JC.

IMO A.752(18), ISO 23601, UL924, ASTM E2030/E2072/E2073, ATPA SS-PS-002-98/SS-PS-004-99, BS 5499-1 2002, NYC Law 26