



JOLIN CORPORATION

大连九霖科技发展有限公司

Tel: +86-411-82479399/ 82479385/ 82479386

Fax: +86-411-82479390

http:// jolingroup.com

Email: jolin@jolingroup.com

Item

Product Description Photoluminescent pigment
 Model YG-C4

Application Scopes

Screen printing ink, brush/roller/spraying paint indoors/outdoors, dip plastic coating, injection/extrusion/casting plastic, silicone rubber molding, etc.

Typical chemical properties

Composition Strontium Aluminate dopped with Europium Dysprosium oxides.
 Insoluble in organic solvents
 Decomposition by Strong acids, strong alkalines, water
 Fastness to heat -40~500°C

Typical physical properties

Appearance Yellowish crystal powder
 Specific gravity 3.6g/cm³
 Bulk Density 1.21g/cm³
 Average Particle size 20-30um 100% passing 250mesh.

Typical luminescent properties

Excitation all visible light and UV light (200~450nm better)
 Glow Color Yellow green (Emitting light Wavelength Peak: 520±2nm)
 Afterglow Intensity after 10min >290 mcd/m²
 60min >38.0 mcd/m²
 600min >2.0 mcd/m²

Afterglow intensity(to 0.32mcd/m²): >5310min under norm DIN67 510

Typical luminance data

Time	10"	1'	2'	3'	4'	5'	10'	15'	20'	30'	40'	50'	60'	90'	120'	180'	300'	600'
mcd/m ²	7332	2238	1362	910	702	577	294	210	139	87	62	47	38	23	18	11	6.6	2.1

Luminance Test Methods	<p>Under Norm DIN67510-1:2009</p> <p>Put sample in opaque container for 24hrs, Temperature: 23±2°C, expose the sample under 1000lx-D65 light source for 5', then turn off the light and test the sample's afterglow luminance at 2', 10', 30', and 60'.</p>
Luminance Test Instruments	<ul style="list-style-type: none"> ○ Charging Light Source D65 Xenon Lamp ○ Charging Lamp Model Toshiba FL20S.D-EDL-D65 ○ Test Instruments Model Luminance Meter: Konica Minolta LS-150 Illuminance Meter: Konica Minolta T-10A

Lifespan: >15years under well packing condition.

Safety:

1. Toxic:

2. Radioactive: NO.

Other data:

1. Using Condition(recommended):
With all colorless, transparent medium, such as paint, coating, resin, etc.
2. Storage Condition: In cool, dry and ventilated place, with temperature -50~60°C
3. Packing: 25kgs /iron pail lined with plastic bags.
G.W.: 26.6kgs, Dim: D31 x H34cm

- 20'Container FCL Q'ty: 11250kgs(palletized)
4. Norm Complied: EN71-3, RoHS, DGM.
5. Norm MEET: PSPA Class-E, JIS-Z9107 JC.
IMO A.752(18), ISO 23601, UL924,
ASTM E2030/E2072/E2073,
ATPA SS-PS-002-98/SS-PS-004-99,
BS 5499-1 2002, NYC Law 26